

FINAL TOUCH ADHESIVE

One component construction adhesive with high initial tack and strong bonding power.

PROPERTIES

- Very strong adhesion on wood, glass, concrete, tile, brick, plaster, some plastics and metal.
- Absorbs vibrations due to its elasticity and therefore usable in moving building elements.
- Isocyanate free and cures bubble free.
- Usable in damp substrates.
- Resistant to weather conditions and humidity.

APPLICATION AREAS

- Fixing baseboard, door fillers, window and door sills.
- Bonding polystyrene cornices and curtain tracks.
- Bonding metal, plastic and wooden building accessories.
- Installing heat and sound insulation boards.
- Bonding mirrors.

PACKAGING

30gr tupe/ 48 box

COLOURS

Black

TECHNICAL DATA

Chemical base	: Moisture Curing STPU polymer
Density	: 1.38 g/cm ³
Application Temperature	: 5C to 35C
Skin Formation Time	: 10-25 min
Curing Speed	: 3mm/24h
Shrinkage	: none
Shore A Hardness	: 50 +/- 5
Tensile strength % (ISO 8339) approx	: 0,9 Mpa
Elongation on Break (ISO 8339)	: > %200
Temperature Resistance	: -40C to 100C

APPLICATION METHOD

All substrates should be free clean, free from dust, oil, grease and any contaminations that could affect the bonding. If the substrates need to be cleaned, use methyl ethyl ketone (MEK), acetone or grease remover. Always be sure that the substrates are dry before the application.

SHELF LIFE AND STORAGE

It must be protected against water, frost, and bad weather conditions. It must be kept on the wooden pallets and cool and dry conditions. The products that are opened must be consumed immediately. It should be stacked maximum 6 layers.

The product's storage is 15 months if the protection conditions shall comply with the above subjects.

SAFETY

Keep out of reach of children. The application should take place in well-ventilated rooms, so that cross linker vapors can escape. During vulcanization, a total of 4% acetic acid is released during this cross-linker vapors may not be inhaled during long periods of time or in high concentrations. Avoid prolonged contact with skin. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice. Avoid contact with food as long as the sealant is uncured.